



Guide to the identification of Wood-boring insects

Introduction

This guide has been produced in response to requests by property owners for an easy-to-use guide for identifying wood-boring insects native to the United Kingdom.

In its current state, it allows the identification of species of wood-boring insects, and indicates whether or not treatment is necessary. Where treatment is necessary, our technical department should be called on **01403 210204** for advice on the most appropriate method of treatment.

We intend to produce an expanded version of this guide to include sections on ascertaining whether infestations are active, and giving detailed information on the different methods of treatment available.

Credits

We would like to thank the Property Guarantee Administration (tel **0870 6071610**) for their help in producing this guide. The PGA offer insurance-backed guarantees for damp-proofing, timber treatment, and tanking. Details are available on the PGA website, www.specifypga.com.

Further Reading

Guides to “Rising damp and its Control” and “Dry Rot and its Control” are available for download from the Safeguard website at www.safeguardeurope.com

©Safeguard Europe Ltd.

COMMON FURNITURE BEETLE

(*Anobium punctatum*)



Adult



Larva



Timbers attacked

Sapwood of hardwoods and softwoods, plywood, wattling.

Damage

Tunnelling in sapwood tends to run along the grain. Tunnels relatively short and contain a loose bore dust. Bore dust feels 'gritty', and under magnification it is uniform in colour and contains 'lemon' shaped pellets.

Exit holes are round, about 1.5 - 2mm diameter.

Life cycle (3+ years)

- i. Adult: Emerge May to August and mate
- ii. Eggs: Laid in cracks, crevices, end grain, old exit holes; white, lemon shaped.
- iii. Larva: Bores straight into wood from egg: feed and grow for 3 or more years. Larvae reach 6mm in length.
- iv. Pupa: Develop below surface of wood. Pupal stage is 6-8 weeks prior to emergence.

Notes:

Damage can be confused with Ambrosia beetle, Wane Edge Borer and Weevil.

Quick Identification:

Short tunnels, lemon shaped pellets present in gritty bore dust.

WANEY EDGE BORER

(*Ernobius mollis*)

Timbers attacked

Partly or fully seasoned softwoods with bark present.

Damage

Confined to the bark with very superficial tunnelling in the outer sapwood; emergence holes rarely further than 15mm from barked area. Holes about 2mm in diameter. Bore dust 'gritty' feel; small 'bun-shaped' light and dark coloured pellets.

Life cycle (1 - 2 years)

- i. Adult : Emerge May - August and lay eggs.
- ii. Eggs: Laid in bark; white, lemon shaped.
- iii. Larva: Bores and grows first in bark; may also superficially attack outer sapwood and this gives rise to the dark and light coloured pellets.
- iv. Pupa: Develops in bark/ sapwood interface 10 days before emergence.


Notes:

Damage is mistaken for Common Furniture Beetle damage. Wane Edge Borer must have bark present.

DOES NOT NEED TREATMENT.

Quick Identification:


Bark present; bun-shaped pellets in bore dust which are dark and light in colour. Holes in bark or close sapwood.



Adult



Larva



AMBROSIA BEETLES

(*Platypodidae, Scolytidae*)

Timbers attacked

Hardwoods and softwoods

Damage

The damage occurs in the forest, the insects attacking standing trees and freshly felled logs, tunnelling into the wood for long distances across the grain. No bore dust. Unlike most woodborers the adult does the tunnelling.

Surface of tunnels are coloured black/blue-black. Holes vary in size depending on which of the Ambrosia beetles caused the damage; many about the same size as furniture beetle holes.

Life cycle:

Varies according to which species of Ambrosia beetle infested the log.

Notes:

The damage is usually confused with Common Furniture Beetle damage but it occurs in the log. These insects cannot infest seasoned timber.

DOES NOT NEED TREATMENT.

Quick Identification:

No bore dust; holes run across the grain long distances (pin test - c/f Common Furniture Beetle). Surface of tunnels coloured black/blue-black.


Since the damage occurred in the log converted wood often cuts holes at an angle which makes them look elongated.

'Pin test'

Ambrosia beetles



Common Furniture beetle



DEATHWATCH BEETLE

(*Xestobium rufuvillosum*)

Timbers attacked

Sapwood and heartwood of hardwoods, usually oak, which have partly decayed. Softwoods are rarely attacked.

Damage

Extensive tunnelling especially towards centre of large dimensioned timber. Exit holes are round, 3mm diameter. Bore dust is bun-shaped and contains pellets visible to the naked eye.

Damage often more extensive than expected from external appearance.

Life cycle (4+ years)

- i. Adult: Emerge March - June; eggs laid 10-20 days after mating.
- ii. Eggs: Laid in cracks and crevices; white, lemon shaped.
- iii. Larva: Crawl prior to boring into wood; feed and grow for up to 12-14 years.
- iv. Pupa: Develop below surface of wood in July - August. Pre-emergent adults wait in pupa chamber until following year

Notes:

Adult beetles can often be found on and beneath infested timbers during emergence period. Will fly but require high temperatures.

Quick Identification:

Large bun-shaped pellets; attacks hardwoods.



Adult



Larva

Average sizes



WOOD BORING WEEVILS

(*Pentarthrum huttoni*, *Euophryum confine*)



Adult



Larva

Timbers attacked

Any wood that is decayed.

Damage

Tunnels run along the grain just below surface, often exposed. Coarse bore dust, 'gritty' feel. Emergence holes are round but with ragged edges. Damage caused by both larvae and adults, both of which may be found in infested wood.

Life cycle (7-9 months)

- i. Adult: Live up to 16 months and feed on wood with larvae.
- ii. Eggs: White, laid on or just below surface.
- iii. Larva: Curved shape, white. Bore extensively along grain. Present for 8-9 months.
- iv. Pupa: Develops just below surface.

Notes

Where weevil damage occurs it is a secondary problem; fungal decay is the primary concern.

Quick Identification

Ragged exit holes; coarse bore dust, tunnels run along grain often breaking the surface. Always in association with fungal decay.



POWDER POST BEETLE

(*Lyctus brunneus*)

Timbers attacked

Sapwood of seasoned wide-pored hardwoods with a high starch content. Timbers over 15 years old not attacked.

Damage

Tunnels tend to run along grain; often causes 'surface' tunnelling where timbers are stacked. Tunnels filled with loose flour-like dust. Round emergence holes 1-2mm diameter.

Life cycle (1-2 years outdoors; 8-10 months indoors)

- i. Adult: Emerge outdoors July - August; anytime indoors.
- ii. Eggs: Laid down open vessels; white, elongated with tail. Hatch in 2-3 weeks.
- iii. Larva: Initially feed and bore along grain.
- iv. Pupa: White; looks more like a beetle than a larva.

Notes

Unlikely to be found in the average domestic environment. Usually a problem in timber yards or stores of hardwoods, e.g., furniture factories. Where found in a building the origin is usually from such storage areas.

Can be confused with Furniture Beetle damage.

Quick Identification


Hardwoods; loose flour-like frass.



Adult



Larva




HOUSE LONGHORN BEETLE


(*Hylotrupes bajulus*)



Adult



Larva



Timbers attacked

Sapwood of seasoned softwood.

Damage

Very severe tunnelling in sapwood; can lead to structural collapse. Frequently only a thin surface veneer of sound wood remains. Exit holes are oval (5mm x 9mm) and tunnels are somewhat flattened and full of 'sausage' shaped pellets.

Life cycle (4+ years)

- i. Adult: Emerge July - September
- ii. Eggs: Laid in fan shaped pattern in cracks in wood; white spindle shaped. Up to 200 laid.
- iii. Larva: Feeds in sapwood for more than 4 years. Causes extensive damage; reaches up to 30mm in length.
- iv. Pupa: Takes place about 3 weeks prior to emergence.

Notes

Damage can be confused with Forest Longhorn damage. Localised distribution around SE England

Quick Identification

Large oval exit holes; loose sausage shaped frass. Tunnels frequently coalesce and not individually identifiable. Ridges on surface of tunnels. Damage internally worse than it appears externally.

FOREST LONGHORNS

(Family: *Cerambycidae*)

Timbers attacked

Softwoods and hardwoods; standing trees, freshly felled and partly dried barked timbers.

Damage

These form a large group of insects and so damage varies in extent and size. Oval exit holes up to 10mm across. Tunnels very discrete, do not merge; tend to run across grain. No bore dust but tunnels may be plugged with a small amount of coarse fibres.

Life cycle

There are large numbers of Forest Longhorns. The life cycle will vary according to the particular Forest Longhorn attacking the wood.


Notes:

These insects attack wood when it is in the forest; they do not attack seasoned wood. Holes seen when wood is sectioned are tunnels and not emergence holes. Damage often mistaken for House Longhorn damage.

NO TREATMENT REQUIRED.

Quick Identification

Discrete flat tunnels; sometimes plugged with a coarse fibre. If bark is present then surface of wood will be attacked and a lot of bore dust under bark only, not in tunnels.



Adult



Larva

